



RSM-1680 - Refined SandMin + #16 - #80



General Information

Presentation	100 lb (sack)	50 lb (sack)	Big Bag	Big Bag
Availability	N/A	✓	✓	✓
Code		RSM-1680S50 RSM-1680P250 RSM-1680T250 RSM-1680P150 RSM-1680T150 RSM-1680NC50	RSM-1680S-BB RSM-1680P2-BB RSM-11T2-BB RSM-1680P1-BB RSM-1680T1-BB RSM-11NC-BB	RSM-1680S RSM-1680P2 RSM-11T2 RSM-1680P1 RSM-1680T1 RSM-11NC
Qualities available*		S1,P1,P2,T1,T2,NC	S1,P1,P2,T1,T2,NC	S1,P1,P2,T1,T2,NC

Colors:

Technical Information

Total Alkalinity (as Na ₂ O) ASTM D-1208.....	0.04%
Bulk Density (ASTM D-1895).....	88.78 lb/ft ³
Moisture.....	0.15%
Acid Insoluble.....	0.14%
pH (ASTM D-1208).....	10.22
Particle Shape (Microscope).....	N/A
Dry Brightness (Hunter Reflectance).....	N/A

Typical Chemical Analysis

Calcium Carbonate.....	95.50%
Magnesium Oxide.....	1.64%
Silica.....	1.91%
Aluminium oxide.....	0.04%
Ferric oxide	0.68%
Potassium Oxide.....	0.01%
Sodium Oxide.....	0.02%
Sulphates.....	> .10 %
Lead	> 10 (mg/kg)



Sieve Information

% Accumulated retained

Mesh #16 - #80 90%

Below - #80 10%

Market Applications

- Textured Stuccos

*Qualities available: S= Supreme P1= Premium 1 P2= Premium 2
T1= Type 1 T2 = Type 2 NC= Non classified

Calcium Carbonate is subject to normal variations related to the deposits from which it is extracted.