



RM-154 - RockMin -15" + 4"



General Information

Presentation	100 lb (sack)	50 lb (sack)	Big Bags	Bulk
Availability	N/A	N/A	✓	✓
Code			RM-154S-BB RM-154P1-BB RM-154T1-BB RM-154P2-BB RM-154T2-BB RM-154NC-BB	RM-154S RM-154P1 RM-154T1 RM-154P2 RM-154T2 RM-154NC
Qualities available*			S, P1, P2, T1, T2, NC	S, P1, P2, T1, T2, NC

Technical Information

Total Alkalinity (as Na ₂ O) ASTM D-1208.....	0.04%
Bulk Density (ASTM D-1895).....	N/A
Moisture.....	0.15%
Acid Insoluble.....	0.14%
pH (ASTM D-1208).....	10.22
Particle Shape (Microscope).....	N/A
Dry Brightness (Hunter Reflectance).....	N/A

Typical Chemical Analysis

Calcium Carbonate.....	95.50%
Magnesium Oxide.....	1.64%
Silica.....	1.91%
Aluminium oxide.....	0.04%
Ferric oxide	0.68%
Potassium Oxide.....	0.01%
Sodium Oxide.....	0.02%
Sulphates.....	> .10 %
Lead	> 10 (mg/kg)



Sieve Information

% Accumulated retained

Size -15" + 4".....	90%
below - 4".....	10%

Market Applications

- Construction Industry
- Landscaping
- Mills (make your own sand)

*Qualities available: S= Supreme P1= Premium 1 P2= Premium 2
T1= Type 1 T2 = Type 2 NC= Non classified

Calcium Carbonate is subject to normal variations related to the deposits from which it is extracted.